

Please insert the following at line 7 on page 1 of the specification.

A4

--BACKGROUND OF THE INVENTION--

Please insert the following at line 25 on page 2 of the specification.

A5

--SUMMARY OF THE INVENTION--

Please insert the following at the top of page 4 of the specification.

A6

--DETAILED DESCRIPTION OF THE INVENTION--

IN THE CLAIMS:

Please replace Claim 5 with the following.

A7

5. (Once Amended, Clean) Moulding composition according to Claim 1 wherein N in the formula (I) means 0.9 to 2.5.

Please replace Claim 6 with the following.

A8

6. (Once Amended, Clean) Moulding composition according to Claim 1 wherein N in the formula (I) means 1 to 1.15.

Please replace Claim 7 with the following.

A9

7. (Once Amended, Clean) Moulding composition according to Claim 1 further containing 0.5 to 60 parts by weight of graft polymer.

Please replace Claim 9 with the following.

9. (Once Amended, Clean) Moulding composition according to Claim 7 wherein the graft polymer is prepared by copolymerization of:

A10

(B.1) 5 to 95 parts by weight of a mixture of,

(B.1.1) 50 to 95 parts by weight of styrene, α -methylstyrene, halo- or alkyl-ring-substituted styrene, C₁-C₈ alkyl

methacrylate, C₁-C₈ alkyl acrylate or mixtures of these compounds, and

AD

(B.1.2)

5 to 50 parts by weight of acrylonitrile, methacrylonitrile, C₁-C₈ alkyl methacrylate, C₁-C₈ alkyl acrylate, maleic anhydride, C₁-C₄ alkyl- or phenyl-N-substituted maleimide or mixtures of these compounds; and

(B.2) 5 to 95 parts by weight of rubber having a glass transition temperature of below -10°C.

Please replace Claim 10 with the following.

10. (Once Amended, Clean) Moulding composition according to Claim 1 containing

A) 40 to 99 parts by weight of at least one of aromatic polycarbonate and polyester carbonate;

B) 0.5 to 60 parts by weight of graft polymer prepared from the copolymerization of,

B.1) 5 to 95 wt.% of one or more vinyl monomers, and

B.2) 95 to 5 wt.% of one or more grafting backbones having a glass transition temperature of <10°C;

C) 0 to 45 parts by weight of at least one thermoplastic polymer selected from vinyl (co)polymers and polyalkylene terephthalates;

D) 0.5 to 20 parts by weight of said phosphorus compound represented by formula (I), and

All

A11

E) 0 to 3 parts by weight of fluorinated polyolefin.

Please replace Claim 11 with the following.

A12

11. (Once Amended, Clean) Moulding compositions according to Claim 1 wherein Y in the formula (I) denotes isopropylidene or methylene.

Please replace Claim 12 with the following.

0274550

A13

12. (Once Amended, Clean) Moulding compositions according to Claim 10 containing a diene rubber, acrylate rubber, silicone rubber or ethylene/propylene/diene rubber or mixtures thereof as the grafting backbone B.2.

Please replace Claim 13 with the following.

0274550

A14

13. (Once Amended, Clean) Moulding compositions according to Claim 1 wherein they contain at least one additive selected from stabilisers, pigments, mould release agents, flow auxiliaries, antistatic agents, fillers and reinforcing materials.

Please replace Claim 14 with the following.

A15

14. (Once Amended, Clean) A method of using the moulding compositions according to Claim 1 for the production of mouldings.

Please replace Claim 15 with the following.

A16

15. (Once Amended, Clean) Mouldings prepared from moulding compositions according to Claim 1.